

## SPECIFICATIONS of: PIETRE NATURALI HIGH TECH (8MM STRUCTURED)

### Supply of porcelain stoneware Ariostea.

#### 1. Product and process features

Porcelain stoneware slabs classifiable as group Impervious P1, frost-proof slabs that resist to chemical attacks, achieved through dry-forming of high-quality mixtures made up of atomized and mixed natural raw materials (kaolin minerals, feldspars).

#### 2. Compliance with Standards

The material, in compliance with the requirements of American standards ANSI A 137.1: June 2021, ANSI A326.3-2021 and ASTM Section 15 Volume 15.02, must meet the following technical features:

ASTM C373 – 18 (Water absorption)

ASTM C499 – 20 (Facial dimension and Thickness)

ASTM C485 – 16 (Warping)

ASTM C502 – 16 (Wedging)

ASTM C482 – 20 (Bond Strength)

ASTM C648 – 20 (Breaking Strength)

ASTM C1505 – 20 (Modulus of Rupture)

ASTM C1895 – 20 (Hardness - Mohs)

ASTM C 1243 – 93 (Deep Abrasion)

ASTM C1026 – 13 (Frost Resistance)

ASTM C650 – 20 (Chemical Resistance)

ASTM C1378 – 20 (Stain Resistance)

ANSI A 326.3 – 2021 (DCOF).

The Quality Control System implemented by the company guarantees the mentioned above features in accordance with UNI-EN-ISO 9001:2015 standards.

The slabs have been checked and evaluated by an independent third-party Body which certifies their compliance to the LEED\_BREEAM.

#### 3. Commercial Description of the Product

|                              |                             |
|------------------------------|-----------------------------|
| <b>Company</b>               | Ariostea                    |
| <b>Collection</b>            | Pietre Naturali High Tech   |
| <b>Product</b>               | Black Ardesia, Wooden White |
| <b>Finish</b>                | Structured                  |
| <b>Rectified/Unrectified</b> | Rectified                   |
| <b>Size in inch</b>          | 24"x48", 24"x24", 12"x24"   |
| <b>Size in cm</b>            | 60x120cm, 60x60cm, 30x60cm  |
| <b>Thickness in mm</b>       | 8 mm                        |

## SPECIFICATIONS of: PIETRE NATURALI HIGH TECH (8MM STRUCTURED)

### Dimensions

Materials supplied in Mono-caliber.

| Nominal Size in mm               | Working Size in mm                              |
|----------------------------------|-------------------------------------------------|
| 600x1200mm, 600x600mm, 300x600mm | 595.8x1195.8 mm, 595.8x595.8 mm, 296.4x595.8 mm |

### 4. Technical Features

| Chemical Physical        | Norms                             | Required Standards                         | Average ICG Production Values <sup>(1)</sup> |
|--------------------------|-----------------------------------|--------------------------------------------|----------------------------------------------|
| Water absorption         | ASTM C 373 - 18                   | Impervious $\leq 0.5$ %                    | $\leq 0.1$ %                                 |
| Thickness Variation      | ASTM C 499 - 20                   | $\pm 0.02$ inch                            | $\pm 0.02$ inch                              |
| Facial Dimension         |                                   | $\pm 0.25$ %                               | $\pm 0.25$ %                                 |
| Warpage Average Diagonal | ASTM C 485 - 16                   | $\pm 0.40$ %                               | $\pm 0.40$ %                                 |
| Warpage Average Edge     | ASTM C 485 - 16                   | $\pm 0.40$ %                               | $\pm 0.40$ %                                 |
| Wedging                  | ASTM C 502 - 16                   | $\pm 0.25$ %                               | $\pm 0.25$ %                                 |
| Bond Strength            | ASTM C 482 - 20                   | $\geq 50$ psi                              | $\geq 50$ psi                                |
| Breaking Strength        | ASTM C 648 - 20                   | $\geq 275$ lbf                             | $\geq 275$ lbf                               |
| Hardness (Mohs)          | ASTM C 1895 - 20                  | Range 0 - 10                               | $\geq 7$ <sup>(3)</sup>                      |
| Frost Resistance         | ASTM C 1026 - 13 (2018)           | No sample must show alterations to surface | No evidence of damage                        |
| Chemical Resistance      | ASTM C 650 - 20                   | Range A / E                                | Class A <sup>(4)</sup>                       |
| Stain Resistance         | ASTM C 1378 - 20                  | Range A / E                                | Class A <sup>(4)</sup>                       |
| Slip Resistance (DCOF)   | ANSI A 326.3 -2021                | $\geq 0.42$                                | $\geq 0.45$ <sup>(2)</sup> Structured        |
| Aesthetic Classification | Visual Evaluation Shade & Texture | Range V1 / V4                              | V2                                           |

#### Note:

(1) -> All values given are for textured/natural finish. Values for different finishes are available upon request.

(2) -> DCOF results referring to textured/natural products are performed with the WET test, while for polished, semi-polished and silky the DCOF test is performed DRY. The values of dynamic friction coefficient (DCOF) shown in the catalogue, web site or sales documents in general, are purely indicative and not binding. Any specific requirement must be confirmed by us at the time of ordering and, in any case, before installation.

(3) -> Mohs result referring to textured/natural finish. For polished/silky finish:  $\geq 6$

(4) -> Chemical and stain resistance are referring to textured/natural finish. For polished/silky finish, tests are provided on request

Rev.1, 01.01.2026

Date: 07.09.2026